

Professional Glue Instructions

Polyurethane glue for repairing boats, trampolines, tents.

Designed for fast and reliable repair of PVC products that are used outdoors, in sea or fresh water. UV resistant

Recommended for:

quick and quality repair in both tourist and domestic environments:

boats and inflatable water rides

trampolines and inflatable sports facilities

car tents and trade pavilions

tourist tents, canoes, kayaks, catamarans

sports and hiking footwear

Application Cold glue method

Mark the spot for the patch. Cut a patch of cloth or PVC film to a size that is 4-5 cm larger than the damaged area.

Clean and degrease the patch and the area to be patched. Apply a thin layer of adhesive to both surfaces to be glued. Dry for 5-10 minutes. Apply a second layer of adhesive and dry for 3-5 minutes. It is important to determine the moment when the glue viscosity begins to disappear (check by finger touch), place the patch into place and press firmly. It is recommended to leave the glue spot under pressure for 3-4 hours. The glued equipment can be used after 3-4 hours.

Application Hot melt adhesive method

Mark the spot for the patch. Cut a patch of cloth or PVC film to a size that is 4-5 cm larger than the damaged area.

Clean and degrease the patch and the area to be patched. Apply a thin layer of adhesive to both surfaces to be glued. Let dry for 5-10 minutes. Apply a second layer of adhesive and dry 5-10 minutes. Heat the glued surfaces to 60 °C, put the patch into place and press firmly. The glued equipment can be used after 20 minutes.

Recommendations and suggestions

Cuts and damages longer than 4 cm are glued on both sides. Cuts and damage longer than 6 cm should be repaired in specialised workshops. Equipment repaired in tourist conditions with greater damage is recommended to be repaired again at the first opportunity with two-component adhesive. Operating temperature of repaired equipment from -40 °C to +80 °C. Repair at the temperature higher than + 10 °C. Store and transport at the temperature from - 10 °C to + 30 °C. Fresh adhesive is removed with spirit or acetone. Maximum effect comes for 24 hours.

Warranty shelf life 18 monthsy

Flammable! Keep out of reach of children. Work should be carried out in a ventilated room.

Production date 12.2018

Manufactured in Ukaina.

Importer: DOVERA SP. Z O.O.

22-100 Chełm ul. Lwowska 51

NIP: 5632430306